



### Product description

PROMAXON® - Typ A is a calcium-silicate based fire protective construction board, resistant to moisture, of stable dimensions, large format and self-supporting. It is produced with quality assurance according to the standard ISO 9001.

### Fields of application

Execution of construction elements for construction and technical fire protection according to EN standard in all the fields of building construction and industrial construction, e.g. in fire resistant partitions, suspended ceilings and trapezoidal steel sheet ceilings.

### Technical data

Nominal dry density (average)	approx. 850 kg/m <sup>3</sup>
Moisture content	approx. 1 - 3% (air dried)
Alkalinity (pH-value)	approx. 9
Thermal conductivity λ	approx. 0.27 W/m.K
Coefficient of resistance to water vapor diffusion μ	approx. 5.0

### Properties

Construction material class	A1, EN 13501-1
Surface properties	one side smooth, one side mildly coarse
Storage	store in a dry location
Disposal	Remains can be disposed off on waste tips for class I construction waste (EWC code 17 01 07)

### Static values

	Bending strength $\sigma_{break}$	Tensile strength $Z_{break}$	Compressive strength $\perp$
(deflection $f \leq l/250$ , safety factor $n \geq 3$ )	4.5 N/mm <sup>2</sup> (in the longitudinal direction of the board)	1.2 N/mm <sup>2</sup> (in the longitudinal direction of the board)	8.0 N/mm <sup>2</sup> (perpendicularly to the board surface)

### Pullout resistances

Type of screws	Pullout resistance of screws ( $Z_{break}$ )				
	Screw for fast construction 3.9 x 55 (G233/355) Knipping	Screw for fast construction 4.2 x 45 (Hi-Lo-thread) Knipping	Screw for fast construction ABC - Spax 4.5 x 40	Screw for fast construction ABC - Spax 4.5 x 50	Screwing nut (type B 3815) RAMPA
Layout	in the board surface	in the board surface	in the board surface	in the board surface	in the board surface
Depth of screwing screws	15 mm	15 mm	15 mm	15 mm	15 mm
Pullout resistance $Z_{break}$	n/a *	n/a *	n/a *	n/a *	n/a *

\* data not available

### Format and weights

Standard formats	Board thickness and weight							
	2500 mm x 1200 mm	8 mm	10 mm	12 mm	15 mm	18 mm	20 mm	25 mm
Dimensional tolerance	thickness	± 0.5 mm						
	length and width	± 0/-3 mm						
Board weight [kg/m <sup>2</sup> ]	± 20 °C, 65 % rel. hum.	approx. 7.0	approx. 8.6	approx. 10.5	approx. 12.5	approx. 14.9	approx. 16.5	approx. 22.1

All data contained in this publication are provided in good faith and are correct at the time of printing. Data are representative of production and are subject to normal production fluctuations, they should not be deemed to constitute or imply any warranty of performance, the user is held responsible for determining the suitability of the products for the given application. Errors and omissions excepted. All drawings and representations remain our exclusive property and cannot be used, totally or in part, without our prior written approval. Excerpts, reproductions, copies, etc. of our publications require our prior approval. This publication renders all previous ones invalid. Our terms of delivery and payment apply in the event of any claim. Promat and Microtherm are registered trademarks. © Copyright Etex NV, Brussels, Belgium. All rights reserved. 2020-09 Etex Industry c/o Microtherm N.V., Industriepark-Noord 1, 9100 Sint-Niklaas, Belgium | T +32 (0)3 760 19 80 | industry@promat.com | www.promat.com/industry